



Argenhelvet Holding

Polymeric Composition **ELE8010A**

DESCRIPTION

Polymer conducting ink **ELE8010A** is specially designed for membrane touch switch application.

TYPICAL APPLICATIONS

- Membrane touch switch application

KEY FEATURES

ELE8010A is designed for:

- Excellent conductivity
- Excellent adhesion

TYPICAL PROPERTIES

- **Solids content:** 65 % typical
- **Viscosity:** 11000 – 20000 cP
- **Sheet resistivity:** < 0.100 Ω / square / 25 µ m
- **Adhesion / Tape Pull:** No Conducting Metal Transfer
- **Pencil hardness:** 2H
- **Operating temperature:** 90 °C

PROCESSING

- **Screen Printing Equipment:** Reel-to-reel, semiautomatic, manual
- **Substrates:** Polyester, polyimide, PVC, ABS, polycarbonate
- **Screen Type:** Polyester, stainless steel
- **Typical Cure Temperature:** Oven 120°C for 30 minutes
- **Clean-up Solvent:** S1008

THINNER

ELE8010A is optimized for screen printing. However, if thinning is necessary, T108 should be used for slight adjustments.

STORAGE

ELE8010A should be stored at 10 – 30°C within the sealed containers. Settling of solids may occur during storage, so the material should be stirred thoroughly prior to use.

SHELF LIFE

ELE8010A has a shelf life of 6 months from date of shipment for factory-sealed containers, stored under our recommended condition.

APPLICATION ASSISTANCE

Our Application Specialists are available to assist you in production start-up with the products. Please contact us for more information.

HEALTH AND SAFETY

Our products are intended for industrial use by trained personnel. The following precautions should be taken when handling the products:

- Read the Material Safety Data Sheet before processing the products.
- Use properly designed engineering controls, such as local ventilation, to limit operating personnel exposures.
- Keep container closed when not in use.
- Do not ingest. Harmful if swallowed.
- If contact with skin occurs, wash affected area immediately with water.

Argenhelvet Holding Limited

Flat/Rm 1305, Universal Trade Centre,
3-5A Arbuthnot Road, Central,
Hong Kong
Tel.: 852 – 3568 4032
Email: sales@argenhelvet.com

The information given and the recommendations made herein are based on our laboratory data and are believed to be accurate but no guarantee of their accuracy is made. In every case, we urge and recommend that purchasers, before using any product in full scale production, make their own tests to determine to their own satisfaction whether the product is of acceptable quality and is suitable for their particular purposes under their own operating conditions. THE PRODUCTS DISCLOSED HEREIN ARE SOLD WITHOUT ANY WARRANTY AS TO MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR ANY OTHER WARRANTY, EXPRESS OR IMPLIED. No representative of ours has any authority to waive or change the foregoing provisions but, subject to such provisions, our engineers are available to assist purchasers in adapting our products to their needs and to the circumstances prevailing in their business.